

SPRAY GALV

#16-845



A cold galvanizing primer that contains 86% Type I inorganic zinc in the dried paint film. Resists oxidation, and the galvanizing protection continues even if scratched. Can be topcoated for maximum durability. Contains an additive which results in less smoke and electrode wear when welding, and cuts faster than 100% zinc rich coatings.

Suggested Uses:

Effective touch-up for
hot dip galvanized surfaces
Chain link fencing
Guardrails

Packaging:

UPC Code	043281001076
Cans per case	6
Shipping weight per case	7 lbs.
Container	16 fluid ounce can
Label weight	15 ounces (425 grams)
Shipping Classification	Consumer Commodity ORM-D, UN 1950
Hazard Class	2.1

Properties:

Flammability	"Extremely Flammable"
Flash point	-40 F
Specific Gravity	0.87
Solids Content	~52%
% Zinc in dried paint film	~86%
MIR value	~0.97, cannot exceed 1.20
HAPs content	~17%
Storage Temperature	40-100F
Application Temperature	50-90F
Durability	Very Good
Abrasion Resistance	Very Good
Heat Resistance	3500 F
Resin System	Modified Epoxy
Shelf life	Guaranteed for 2 years
Food contact rating	Category 21: Acceptable

Dry Time*:

To touch	5 minutes
To topcoat	20 minutes

*At 720 F, 50% humidity,
1.5 mil thickness

**Curing/Recoat time is extended with
multiple coats and excessively thick
coats**

Gloss*: Flat, <15*

*as measured on a 600 gloss meter

Meets or exceeds the following performance requirements:

ASTM A780
MIL-P-26915C
MIL-P-46105
DOD-P-21035A
SSPC-Paint 20